



INTERTAC – Modified

Intertac is a Solvent Free, Low Odour, Low VOC Pressure Sensitive adhesive specially formulated for installing glass back carpet tiles.

Surface Preparation

To be in accordance with AS/NZ 2455.1.2007 "Textile floor coverings – installation practice General", AS/NZ 2455.2.2007 "Textile floor coverings – installation practice Carpet tiles.

All surfaces to be bonded to should be dry, smooth, sound and clean.

Subfloors should be free from wax, grease, paints previously used adhesive, hydrostatic pressure, polishes and PVC base membranes

All concrete floors should be tested for moisture content in accordance the above Australian Standards prior to the undertaking surface preparation or installation of floorcoverings.

The minimum subfloor temperature before commencing surface preparation and adhesive application is 10C.

Its recommended that all absorbent concrete subfloors be primed with GS 400 floor and wall primer prior to the application of adhesive.

Application & Spread Rate

For securing Glasbac carpet tiles a log nap roller with a pile height of no less than 10mm is recommended.

The use of a long nap roller with a pile height of no less than 10mm can achieve an approx spread rate of 10-14 square metres per litre.

In some cases a higher spread rate on application can be achieved when applied over low absorbent substrates.

Coverage when applying adhesive with a 1.6mm notched V1 notched trowel will achieve up to 5 square metres per litre.

Intertac adhesive is used in dry mode, allow the adhesive to dry and become clear, this will limit the transfer of the adhesive to the back of the carpet tiles therefore enabling them to be relayed or repositioned with a clean backing.

A stronger bond can be achieved by laying the material into the adhesive film just prior to it drying completely, this will cause some transfer onto the back of the material.

Clean Up

Clean tools immediately after use with warm soapy water.

Dried adhesive on tools can be softened and lifted with Roberts 550 Latex/Acrylic Adhesive Remover.

Typical Properties

Appearance	Green Liquid
Base	Acrylic
Viscosity	Trowellable/ Rollable
Shelf Life	12 months in sealed container at 20°C.
Packaging	15 litres

Materials Safety Data Sheet available upon request

Storage

Recommended to be at temperatures between 10C and 30C, keep in well ventilated areas away from sources of heat and direct sun light.

Shelf Life

12 months in unopened containers and store under the appropriate conditions above.

November 2010

The application, use and processing of our products is the responsibility of the user. Any technical or other advice, information or data provided by us, whether verbally, in writing or by way of trials or tests, is given without guarantee or warranty. Refer to Material Safety Data Sheets for information on Storage & Handling, Health and Safety, and Transport.

RLA POLYMERS PTY LTD

ACN 004 709 915

215 Colchester Road, Kilsyth, Victoria 3137 Australia
P.O. Box 147, Kilsyth, Victoria 3137 Australia
Telephone: (03) 9728 1644 • Facsimile: (03) 9728 6009

E-mail: info@rlapolymers.com.au • Web: www.rlapolymers.com.au



67 Dalgety Drive (P.O. Box 97-575)
Manukau City, Auckland, New Zealand
Telephone: (9) 268 0301
Facsimile: (9) 268 0305