

## SYDNEY CARPET LABORATORY

OF INTERFACE AUST, PTY LIMITED - ABN 39 000 692 026

34 AIRDS ROAD, MINTO NSW 2566 - TEL: (02) 8706 4600 FAX: (02) 8706 4617

## **TEST REPORT**

Client: Interface Australia PTY LTD 34 Airds Road Minto NSW 2566 Test Report No: D11-15-005

Sample Received date: 03/12/2015

Test Date: 10/12/2015 Report Date: 15/12/2015

Sample Description: Client Reference: "Time Warp Collection (Amplified Time, Chenille Time,

Happening Time, Psychedelic Time)" 100% Solution Dyed Nylon 66

610g/m<sup>2</sup> on a CushionbacRE Backing

AS ISO 9239.1 – 2003: Reaction to Fire Tests for Floorings – Determination of the Burning Behaviour Using a Radiant Heat Source

## **Results Summary**

CHF Value	Sample 1	Sample 2	Sample 3	Mean	
Length	4.5	4.5	4.0	4.3	kW/m <sup>2</sup>
Width	4.6	-	-	-	kW/m <sup>2</sup>
Omala Walaa	0	0	0		
Smoke Value	Sample 1	Sample 2	Sample 3	Mean	
Length	257	273	278	269	%.min
Width	274	-	-	-	%.min
Melting				Yes	
Blistering				Yes	

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BS EN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each Specimen was adhered to a substrate of 9mm thick fibre cement board using Intertac adhesive.

Page 1 of 9

This report may not be reproduced except in full and shall be rendered void if amended or altered.