Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051

AWTA PRODUCT TESTING

Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

CLIENT : INTERFACE AUSTRALIA PTY LTD PO BOX 158 HORSLEY PARK NSW 2175			TEST NUMBER : 7-573735-AN ISSUE DATE : 14/07/2010 PRINT DATE : 10/08/2012 ORDER NUMBER : 26861			
Colc	ents Ref: "Suit ted tip sheared our: Grey fox pile height	l loop pile	e carpet ti	le		
Material Specification Nominal composition: 1 Nominal total pile mas Nominal backing: Cushi	.00% solution d ss: 577g/m2	yed Nylon				
ASISO 9239.1-2003 Part 1	Determina		ests for Fl ne Burning at Source			
Date of sample arrival Date tested: Results:	13/07/201	.0	Flux / Crit 3	ical Rad: Mean	ant Flux)	
Length	4.1	4.0	4.0	4.0	kW/m2	AT A PARTY
Width	4.3	HERE	886118	19523	kW/m2	I S S S S S S S
Contractor Contractor	Tereseletet	Smo	oke Value	i e te te	A GORDAN	CECEL S
Length Width	257 263	253	177	229	% min % min	STEPER'S
board using Roberts 65 The test results relat under the particular c sole criterion for ass	e to the behav conditions of t	iour of th he test, t	ne test spe chey are no	cimens of t intende	ed to be the	
				Ň		
181891 2		相關的	( END OF	REPORT	) PAGE 1	112212
Australian Wool Testing Authority Ltd Copyright - All Rights Reserved	-Chemical Te	sting of Textiles 8	& Related Products & Related Product	:	g Authorities, Australia, for: Accreditation No. 983 Accreditation No. 985	r h
i	This document is issued identifying descriptions ha warranty, implied or otherw	perature Measure in accordance w ave been provided ise, as to the sourd	ith NATA's accred by the client unlested same	ss otherwise st les. The above	Accreditation No. 1356 nents. Samples, and their ated. AWTA Ltd makes no est results relate only to the nd shall be rendered void if	

APPROVED SIGNATORY

JADY

HAEL A. JACKSON B.Sc.(Hons)

0204/11/06