

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3037 Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

Client : Interface Au 34 Airds Roa Minto NSW 3			lssue Print	Number : Date : Date : r Number :	15-00213 28/05/201 28/05/201 36992	15
Sample Description	Nominal Mass per Unit Area/Den	Solution Dyed Ya	rn Nylon 6 n2 On a Cushi	onbac Backir	ng	
5/ISO 9239.1-2003	Reaction to Fire Tests for Floor Radiant Heat Source	ings. Determinati	ion of the Bur	ning Behavi	our using a	
	Date of Sample Arrival	06/05/2015				
	Date Tested 26/05/2015					
	CHF Value	1	2	3	Mean	
	Length	4.6	4.1	4.3	4.3	kW/m²
	Width	4.6	-	-	-	kW/m²
	Smoke Value	1	2	3	Mean	
	Length	301	316	286	301	%.min
	Width	321	-	-	-	%.min
	Melting				Yes	
	Blistering				Yes	
	The test results relate to the beh conditions of the test, they are no hazard of the product in use.		•	•	•	

Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

25289 4780 Page 1 of 1 Australian Wool testing Authority Ltd Copyright - All Rights Reserved Accredited for compliance with ISO/IEC 17025 C - Chemical Testing Accreditation No 983 NATA - Mechanical Testing · Accreditation No 985 Performance & Approvals Testing 1356 : Accreditation No Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



