Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

WTA Product Testing

P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

7-598116-AN CLIENT : INTERFACE AUSTRALIA PTY LTD TEST NUMBER : : 27/06/2014 34 AIRDS ROAD ISSUE DATE : 27/06/2014 MINTO NSW 2566 PRINT DATE ORDER NUMBER : 35562 SAMPLE DESCRIPTION Clients Ref: "Lofty" Multi-level tufted carpet tile Colour: Multi-colour pattern Approximate Pile Height: 4mm to 9mm Material Specification: Nominal Composition: 100% Solution Nylon 6 Nominal Total Pile Mass: 882 g/m2 Nominal Backing: Glasbac Backing Reaction to Fire Tests for Floorings Determination of the Burning Behaviour ASISO 9239.1-2003 using a Radiant Heat Source Date of sample arrival: 24/06/2014 Date tested: 26/06/2014 CHF Value Results: 1 2 3 Mean 3.7 4.5 4.1 4.1 kW/m2Length 4.8 Width kW/m2 Smoke Value 1 2 3 Mean 162 153 168 161 Length % min Width 173 % min Observations: Melting, Blistering Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use 207915 1 END OF REPORT) PAGE 1 (© Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



 This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:

 -Chemical Testing of Textiles & Related Products
 :
 Accreditation No.
 983

 -Mechanical Testing of Textiles & Related Products
 :
 Accreditation No.
 983

 -Heat & Temperature Measurement
 :
 Accreditation No.
 1356

LIMITED

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if ammended or altered. This document the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd. Machin

APPROVED SIGNATORY

HAEL A. JACKSON B.Sc.(Hons)

0204/11/06