

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240. North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Interface 34 Airds			Number : Date :			
Minto NSW 2566			Print Date 9/12/2014 Order Number 35730			
Sample Description	Clients Ref : "Sidetrack" 100% Solution Dyed Nylon 66 543g/m2 On a Glasbac Backing					
S/ISO 9239.1-2003	Reaction to Fire Tests for Flooring Radiant Heat Source	ıs. Determinati	ion of the Bur	rning Behavi	our using a	
	Date of Sample Arrival	07/11/2014				
	Date Tested	08/12/2014				
	CHF Value	1	2	3	Mean	
	Length	6.4	6.0	6.2	6.2	kW/m²
	Width	7.0	-	-	-	kW/m²
	Smoke Value	1	2	3	Mean	
	Length	173	177	190	180	%.min
	Width	126	-	-	-	%.min
	Melting				Yes	
	Blistering				Yes	

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.


Sample was conditioned in accordance with BSEN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

10354

1525

Australian Wool testing Authority Ltd Copyright - All Rights Reserved C



Chemical Testing - Mechanical Testing Performance & Approvals Testing

Accredited for compliance with ISO/IEC 17025

Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Accreditation No Accreditation No : Accreditation No

983 985 1356

Page 1 of 1





APPROVED SIGNATORY