



TEST REPORT

Client: Interface Australia PTY LTD
34 Airds Road
Minto NSW 2566

Test Report No: D11-19-039
Sample Received date: 19/08/2019
Test Date: 28/08/2019
Report Date: 29/08/2019

Sample Description: Client Reference: "WORKS STREAM"
100% Solution Dyed Nylon 6
475g/m² on a CushionBacRE Backing

AS ISO 9239.1: Reaction to Fire Tests for Floorings – Determination of the Burning Behaviour Using a Radiant Heat Source

Results Summary

CHF Value	Sample 1	Sample 2	Sample 3	Mean	
Length	3.4	-	-	-	kW/m ²
Width	3.2	3.0	3.2	3.1	kW/m ²
Smoke Value	Sample 1	Sample 2	Sample 3	Mean	
Length	206	-	-	-	%.min
Width	212	207	219	213	%.min

Melting Yes
Blistering Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BS EN 13238 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each Specimen was adhered to a substrate of 9mm thick fibre cement board using Intertac adhesive.

END OF REPORT