



## TEST REPORT

Client: Interface Australia PTY LTD  
34 Airds Road  
Minto NSW 2566

Test Report No: D11-16-10-069  
Sample Received date: 06/10/2016  
Test Date: 11/10/2016  
Report Date: 12/10/2016

Sample Description: Client Reference: "ON100"  
100% Solution Dyed Nylon 6  
746g/m<sup>2</sup> on a Glasbac Backing

AS ISO 9239.1 – 2003: Reaction to Fire Tests for Floorings – Determination of the Burning Behaviour Using a Radiant Heat Source

### Results Summary

CHF Value	Sample 1	Sample 2	Sample 3	Mean
Length	3.4	-	-	- kW/m <sup>2</sup>
Width	3.2	3.6	3.2	3.3 kW/m <sup>2</sup>

Smoke Value	Sample 1	Sample 2	Sample 3	Mean
Length	203	-	-	- %.min
Width	222	212	211	215 %.min

Melting Yes  
Blistering Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BS EN 13238:2001 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each Specimen was adhered to a substrate of 9mm thick fibre cement board using Intertac adhesive.