


Installation



All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com/disclaimer.

Product Hip Over History **Backing** GlasBac™

Product Specifications

| | |
|-------------------------|---|
| Product Number: | 127220AB00 |
| Product Construction: | Tufted Sheared |
| Custom Sample: | 264911-006 |
| Yarn System: | 100% Recycled Content Type 6 Nylon |
| Yarn Manufacturer: | Aquafil |
| Dye Method: | 100% Solution Dyed |
| Recycled Content: | |
| Post Industrial Range: | 64% - 64% |
| Post Consumer: | 11% |
| Total Recycled Content: | 75% - 75% |
| Soil/Stain Protection: | Protekt ² |
| Antimicrobial: | (AATCC 138 Washed) (AATCC 174 Parts 2&3) Intersept® |

| | Imperial | Metric |
|---------------------------|-----------------------|------------------------|
| Tufted Yarn Weight: | 24 oz/yd ² | 814.0 g/m ² |
| Machine Gauge: | 1/10 in | 39.4 ends/10 cm |
| Pile Height: | 0.17 in | 4.3 mm |
| Pile Thickness: | 0.110 in | 2.8 mm |
| Stitches | 7.50 /in | 29.53 ends/10 cm |
| Pile Density: | 7855 | |
| Traffic Classification: | Severe | |
| Fiber Modification Ratio: | 1.9 To 2.2 | |
| Size: | 19.69 in X 39.37 in | 50 cm X 1 m |

Performance Specifications

| | |
|------------------------|--|
| Radiant Panel: | (ASTM E-648) Class 1 |
| Smoke Density: | (ASTM E - 662) ≤450 |
| Lightfastness: | (AATCC 16 - E) ≥ 4.0 @ 60 Afu's |
| Static: | (AATCC - 134) < 3.0 Kv |
| Dimensional Stability: | AACHEN Din 54318 <.10% |
| Flammability: | Passes Methenamine Pill Test (Doc-Ff1-70) |
| Standard Backing: | GlasBac Tile |
| Backing Options: | GlasBac Tile, GlasBacRE Tile, CushionBac Renew™ Tile |